



3349-ES CONCRETE CRACK FILLER

SPECIALTIES FOR MAINTENANCE AND SANITATION SINCE 1947



Restores the integrity of the slab and protects against further deterioration.

- *New Pourable Formula*
- *Fills Cracks*
- *Justifies Slabs and Repairs Joints*
- *Super Strong Modified Epoxy*

REPAIRS CONCRETE SURFACES

POURABLE formula makes filling of cracks and expansion joints easy and economical.

SUPER STRONG—Impact resistant, shock resistant and vibration absorbent.

IMPROVES sanitation with an impervious surface that resists penetration by bacteria.

WITHSTANDS foot traffic in 4 hours, heavy wheel traffic in 16 hours.

MIXING is easy. Simply stir one 24 oz. can of hardener into one gallon of aggregate. Do not attempt to mix smaller quantities. The two components may be mixed and applied by casual labor.

CHEMICAL RESISTANT—Foremost 3349-ES is more resistant to oils, chemicals and moisture than regular concrete. It has the tensile strength and adhesion to resist freeze-thaw lifting and durability to withstand weathering. Indoors or out, Foremost 3349-ES won't loosen, crack or shrink under stress.

— NOTE —

Foremost 9577 Concrete Crack Filler Dispenser Pictured Above.

**Packaged in Kits of 3—12/1 gallons Foremost Aggregate
3—12/24 oz. cans Foremost Liquid Hardener**

Rev. 4-23-14

Toll Free: 800-238-5150
Local: 901-363-4340
Fax: 901-375-3600

Delta Foremost Chemical Corp.
3915 AIR PARK ST. • P.O. BOX 30310 • MEMPHIS, TENNESSEE 38130-310

Visit our Web Site at:
www.deltaforemost.com



TECHNICAL DATA

FOREMOST 3349-ES CONCRETE CRACK FILLER

Rev. 12-11-97

DESCRIPTION: Foremost 3349-ES Concrete Crack Filler is a select two (2) component epoxy formulation that offers binding qualities not found in similar products. It pours right into cracks and joints to seal out destructive chemicals, water and frost. Foremost 3349-ES Concrete Crack Filler is self-priming, self-leveling, non-shrinking and won't become brittle. It is a 100% epoxy compound that absorbs steel wheel impact.

COVERAGE: 38 linear feet per gallon (1" x ½").

APPLICATION: Foremost 3349-ES Concrete Crack Filler is recommended for fast and economical repairs to cracked concrete, sidewalks, driveways, broken curbs, steps, ledges, chuck holes, potholes, etc.

DIRECTIONS: NOTE: Do not contaminate the material with water before applying and do not apply out of doors if rain is likely or if temperature is below 40°F.

1. Surface to be coated should be cleaned and free from oil and grease. Sweep thoroughly to remove dirt and loose debris.
2. Mix thoroughly by adding one (1) gallon of Foremost 3349A-ES Concrete Crack Filler to 24 ounces of Foremost 3349B-ES Concrete Crack Filler. Continue mixing until you have a uniform, thin, workable mixture.
3. Pour into suitable dispenser or pour directly from mixing container.
4. Pour mixture into cracks, holes, joints, etc., and smooth out if necessary with regular cement working tools.
5. Tools can be cleaned with detergent and water.
6. Allow the areas to dry 4 hours before using for foot traffic and overnight for heavy traffic.
7. The pot life on this mixture is one (1) hour. Do not mix more material than can be applied within 45 minutes.

PRECAUTIONS: **KEEP OUT OF REACH OF CHILDREN.** Avoid contact with face, skin or eyes. May cause skin irritation. May be harmful if swallowed. Do not take internally.

FIRST AID: EYES: Flush eyes with plenty of water for at least 15 minutes. Get medical attention.

SKIN: Wash with soap and water. Get medical attention if irritation occurs. Remove and wash contaminated clothes. **INGESTION:** If swallowed, induce vomiting. If large amounts are ingested, see physician immediately.

Before using this product, read the Material Safety Data Sheet (MSDS) for more detailed information regarding safe handling.